

Acoustic & Sonic Inc

2298 NW 82 AVE., Doral, FL 33122

Phone: (305) 436-8360 | (786) 423-1756 | Fax:(305) 436 8585

Email: info@acousticsonic.com | www.acousticsonic.com

BLACK ACOUSTIC FIBERGLASS ROLL

Insulation Properties:

- *High Thermal and Acoustical Performance*
- *Resistant to Air Erosion*
- *Ease of Handling, Fabrication, and Installation*
- *Abuse Resistant*

Product	Density	Thickness	Octave Band Center Frequencies, Hz						
	Pcf (kg/m3)	In (mm)	125	250	500	1000	2000	4000	NRC
Black	1.5 (24)	1.0 (25)	0.16	0.37	0.66	0.83	0.91	0.91	0.70
Fiberglass Roll	1.5(24)	1 1/2(38)	0.12	0.41	0.82	0.95	1.01	1.01	0.80

Acoustic Sonic Inc.